



Technical Installation Specification

Sub Floor Requirements / Preparation

Superfloor can be installed over existing flooring, structurally sound plywood , gypsum topping and concrete sub floors. Smooth and Flat - Remove any high spots with a terrazzo grinder or sander and fill any low spots with a good quality cement based patch mix.

Concrete Sub Floors

Concrete should be at least 60 days old. Inspect the concrete before installing flooring over it. First inspect for any wetness at the base of the drywall or for visible signs of moisture on the concrete. Second, test for moisture.

Moisture Testing: Impacta Technical Services requires the use of moisture tests on all concrete and wood sub floors. Sub floor moisture percentages should not exceed the flooring manufacturer's or Impacta Technical Services recommendations of 3-4 pounds per 1,000 square feet over 24 hours, whichever is lowest.

~ Superfloor should not be installed if the relative air humidity is above 75%.

~ Superfloor should not be installed if the HVAC is not operational with a maintained temperature of at least 65° Fahrenheit.

Typical Installation Times of Redupax in man hours

Product	Small rooms / bathrooms 40-110 sf	Average size rooms <220 sf	Larger Size rooms 220-330 sf	Wide open Large rooms 330 sf+ each 100 sf
Superfloor	½ man hour	1 man hour	1 ½ man hours	1 ½ + ½ man hour for every 110 sf more

~ If you have questions regarding installation of Superfloor please call our technical line at 800-569-1294 ask for the Impacta dept.

